

MANUFACTURES OF INDUSTRIAL FILTER BAGS

---

## Polyester MNO data sheet

<b>EH Filters part number</b>	<b>Type</b>	<b>Aperture opening</b>	<b>Thread diameter</b>	<b>Open area</b>	<b>Weight</b>	<b>Role width</b>	
Number	PE	MICRON	MICRON	%	g/m <sup>2</sup>	INCH	CM
TBA	PE	44	39	28	45	65"	165
M-PEMNO 0003	PE	60	39	36	38	65"	165
TBA	PE	74	55	33	57	65"	165
M-PEMNO 0004	PE	152	80	42	70	65"	165
M-PEMNO 0006	PE	101	55	41	47	65"	165
M-PEMNO 0008	PE	225	120	43	106	65"	165
TBA	PE	325	150	47	270	65"	165
M-PEMNO 0010	PE	400	150	49	116	65"	165
M-PEMNO 0012	PE	425	250	40	240	65"	165
M-PEMNO 0015	PE	580	250	48	193	65"	165
M-PEMNO 0018	PE	760	350	47	283	65"	165

## Operating Temperatures

Operating temperature <200°C  
Softening point 220-240°C  
Melting Point 250-260°C