

MANUFACTURES OF INDUSTRIAL FILTER BAGS

Polyester Mono Filament data sheet

EH Filters part number	Type	Aperture opening	Thread diameter	Open area	Weight	Role width	
Number	PE	MICRON	MICRON	%	g/m ²	INCH	CM
M-PEMNO 0001	PE	25	31	23	45	61"	157
M-PEMNO 0002	PE	44	39	28	45	65"	165
M-PEMNO 0003	PE	60	39	36	38	65"	165
M-PEMNO 00035	PE	74	55	33	57	65"	165
M-PEMNO 0004	PE	152	80	42	70	65"	165
M-PEMNO 0006	PE	101	55	41	47	65"	165
M-PEMNO 0008	PE	200	80	43	106	65"	165
M-PEMNO 0009	PE	300	120	51	210	65"	165
M-PEMNO 0010	PE	400	150	49	116	65"	165
M-PEMNO 0012	PE	425	250	40	240	65"	165
M-PEMNO 0015	PE	580	250	48	193	65"	165
M-PEMNO 0018	PE	760	350	47	283	65"	165

Weave

Plain heat set

- Satin weaves are available in certain micron ratings contact us for details.

Operating Temperatures

Operating temperature <200°C
Softening point 220-240°C
Melting Point 250-260°C

Material composition 100% polyester

For compatibility reference a Polyester chemical compatibility chart.

